






-  WEARING COURSE - 30mm THICK SIZE 10 ASPHALT
-  INTERMEDIATE COURSE - 60mm THICK SIZE 20 TYPE N ASPHALT
-  BASE COURSE - 60mm THICK SIZE 20 TYPE N ASPHALT
-  50mm MIN DEPTH 25MPA CONCRETE
-  150mm MIN DEPTH 4% CEMENT TREATED CRUSHED ROCK (CLASS 2).

GENERAL NOTES

1. PITCHERS ARE NOMINALLY 300*225*150mm.
2. PITCHER CHANNEL TO BE LAID IN STRETCHER BOND PATTERN.
3. THIS DRAWING IS TO BE READ IN CONJUNCTION WITH COUNCILS SPECIFICATION "CONSTRUCTION OF PITCHER KERB & CHANNEL AND PRAM CROSSINGS".
4. DAMAGED AND UNSUITABLE BLUESTONE BLOCKS(PITCHERS) TO BE REPLACED
5. ALL BLUESTONE JOINTS TO BE NO MORE THAN 15mm WIDE.
6. ALL MORTAR JOINTS TO HAVE A BRUSH FINISH
7. PREPARATION OF SUBGRADE AS PER VICROADS SPECIFICATION SECTION 204 CLAUSE 204.15.
8. MINIMUM LONGITUDINAL GRADE OF LANE WAY TO BE 0.3%.
9. THE NEED FOR AN A.G PIPE TO BE DETERMINED BY CONTRACT SPECIFICATION OR SUPERVISING ENGINEER.

WHERE REQUIRED TO BE USED, CONCRETE GROUT SHALL CONSIST OF:

- 1 PART CEMENT
 - 1.5 PARTS SAND OR APPROVED GRIT
 - 2 PARTS FINE TOPPINGS
 - 5 PARTS 10mm TOPPINGS
- ABLOX CEMENT BLACK COLOURING IS TO BE ADDED AT THE RATE OF 8% BY WEIGHT OF CEMENT CONTENT
- CEMENT MORTAR SHALL CONSIST OF:

- 1 PART CEMENT
 - 3 PARTS SAND OR APPROVED GRIT
- ABLOX CEMENT BLACK COLOURING IS TO BE ADDED AT THE RATE OF 8% BY WEIGHT OF CEMENT CONTENT(EQUIVALENT)
- ALL PITCHING AND/OR KERBING, WHEN FINISHED, SHALL BE PROPERLY BACKED 25MPa CONCRETE

Yarra Standard: YSD46
Drawing Title:

TYPICAL LANE WAY : BLUESTONE
PITCHER SPOON DRAIN WITH
ASPHALT FLANKS

Scale : N.T.S
Updated 12/12/07

